AMENDMENTS TO THE CLAIMS

This listing of Claims shall replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1. (Currently Amended) A method for fabricating fire retardant composite panels comprising:

creating a water-based slurry comprising a boron salt solution and a plurality of suspended boron salt particles, wherein said creating comprises adding boric acid and borax pentahydrate to water;

adding an adhesive to a ligneous material; and

introducing said water-based slurry to said ligneous material for fire retarding thereof, wherein said introducing is performed separately from said adding.

- 2. (Previously Presented) The method as recited in Claim 1, wherein said fire retardant composite panel is selected from the group consisting of particle board, medium density fiber board, oriented strand board, laminated veneer lumber, and agri-boards.
- 3. (Cancelled)
- 4. (Currently Amended) The method as recited in Claim [[3]] 1, wherein said creating further comprises selecting a potential of hydrogen (pH) for said waterbased slurry of substantially between 4.5 and 5.2.

PINE-001 Application No. 10/600,567 Page 2

Examiner: Dixon, M.

Group Art Unit: 1774

5. (Currently Amended) The method as recited in Claim [[3]] 1, wherein said

creating further comprises reducing a particle size of a portion of said plurality of

suspended boron salt particles.

6. (Original) The method as recited in Claim 1, wherein said fire retardant

composite panel is substantially compliant with the American Society for Testing

and Materials (ASTM) E-84 class 1 standard for fire retardance.

7. (Original) The method as recited in Claim 6, wherein said fire retardant

composite panel has a density of between 40-48 pounds per cubic foot (lb/ft³).

8. (Original) The method as recited in Claim 7, wherein said fire retardant

composite panel has an internal strength of 100 pounds per square inch (psi) or

greater.

9. (Original) The method as recited in Claim 6, wherein said fire retardant

composite panel comprises approximately 1.75% boron w/w expressed as "B" on

an "as is" basis, or less.

10-34. (Cancelled)